

PATENT ABSTRACTS OF JAPAN

(11)Publication number : 05-256968

(43)Date of publication of application : 08.10.1993

(51)Int.Cl.

G21B 1/00
C22C 27/04

(21)Application number : 04-055383

(71)Applicant : HITACHI LTD

(22)Date of filing : 13.03.1992


(72)Inventor : SAKURAI SHIGEO
MIZOGUCHI TADANORI

(54) FIRST WALL OF FUSION REACTOR

(57)Abstract:

PURPOSE: To endure high heat load and make the improvement of erosionproof characteristic by forming a thin film between a metal material and a high melting point member and laminating to joint an intermediate layer wherein a ratio of components of them changes in steps.

CONSTITUTION: A surface 2 facing a first fusion wall 1 is formed of a high melting point metal of 3000°C or higher, for instance, a thin film 3 of tungsten. A next film 4 is jointed with the high melting point metal and a member material for cooling, for instance, another thin film composed of 80% tungsten and 20% copper. In the following, components are changed successively and a film 6 nearest to copper 7 used for a heat tank material 7 composed of a member material for cooling is jointed with a thin film composed of 40% tungsten and 60% copper. In addition, a pipe 8 penetrates the heat tank material 7 and cooling water is allowed to flow therein. The relation to a thermal expansion coefficient by the copper component in tungsten is linearly proportional. Accordingly, a ratio of the copper composition component is inclinedly changed to joint for the purpose of lessening generated thermal stress, having a high degree of expansion, fitting a joint face and making possible the joint of less defects.



LEGAL STATUS

[Date of request for examination]

[Date of sending the examiner's decision of rejection]

[Kind of final disposal of application other than the examiner's decision of rejection or application converted registration]

[Date of final disposal for application]

[Patent number]

[Date of registration]

[Number of appeal against examiner's decision of rejection]

[Date of requesting appeal against examiner's decision of rejection]

[Date of extinction of right]

Copyright (C); 1998,2003 Japan Patent Office